



**Product Information** 



Double-sided non-woven tape with differential adhesion level

### **Product Description**

tesa<sup>®</sup> 4914 is a translucent double-sided self-adhesive tape consisting of a non-woven backing and a tackified acrylic adhesive with lower coating weight on the open side.

tesa® 4914 features especially:

- Open side: lower adhesion level
- Covered side: higher adhesion level
- Foamed adhesive coating with high initial tack
- Excellent performance on rough surfaces

### **Product Features**

- Asymmetrical product design with superior adhesion on liner-covered side
- Excellent performance on rough surfaces like leather and textiles
- Reliable bond, often also on low surface energy surfaces
- Low VOC according to VDA278 analysis
- Flame retardant according to FAR/JAR/CS 25.853(a) Appendix F part I (a)(1)(ii)

### **Application Fields**

- Mounting of car roof linings in car production
- Lamination of foamed materials in combination with smooth materials on the open side

non-woven

250 µm

PE

tackified acrylic

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### **Product Construction**

| <ul> <li>Back</li> </ul> | king |
|--------------------------|------|
|--------------------------|------|

- Type of adhesive
- Type of liner
- Total thickness

- Color
- Color of liner
- Thickness of liner
- Weight of liner
- translucent red 80 μm 92 g/m<sup>2</sup>





# **Product Information**

## **Properties/Performance Values**

| • | Elongation at break     | 3 %    |
|---|-------------------------|--------|
| • | Tensile strength        | 8 N/cm |
| • | Ageing resistance (UV)  | good   |
| • | Chemical Resistance     | good   |
| • | Humidity resistance     | good   |
| • | Softener resistance     | good   |
| • | Static shear resistance | low    |

#### **Adhesion to Values**

| ٠ | ABS (initial)                     | 5.6 N/cm |
|---|-----------------------------------|----------|
| • | ABS (after 14 days)               | 7.7 N/cm |
| ٠ | ABS (covered side, after 14       | 7.6 N/cm |
|   | days)                             |          |
| • | ABS (covered side, initial)       | 7.6 N/cm |
| • | Aluminium (initial)               | 5.2 N/cm |
| ٠ | Aluminium (after 14 days)         | 6.3 N/cm |
| • | Aluminium (covered side, after    | 8 N/cm   |
|   | 14 days)                          |          |
| • | Aluminium (covered side, initial) | 7.8 N/cm |
| • | PC (initial)                      | 5.8 N/cm |
| • | PC (after 14 days)                | 7.4 N/cm |
| • | PC (covered side, after 14 days)  | 8.2 N/cm |
| • | PC (covered side, initial)        | 8.1 N/cm |
| • | PE (initial)                      | 3.2 N/cm |
| • | PE (after 14 days)                | 3.4 N/cm |
| ٠ | PE (covered side, after 14 days)  | 5.3 N/cm |
| ٠ | PE (covered side, initial)        | 4.2 N/cm |
| • | PET (initial)                     | 4.8 N/cm |
| ٠ | PET (after 14 days)               | 6.2 N/cm |
|   |                                   |          |

| • | Static shear resistance at 23°C | low    |
|---|---------------------------------|--------|
| • | Static shear resistance at 40°C | low    |
| • | Tack                            | good   |
| • | Temperature resistance long     | 80 °C  |
|   | term                            |        |
| • | Temperature resistance min.     | -40 °C |
| • | Temperature resistance short    | 140 °C |

term

| • | PET (covered side, after 14 days) | 7.9 N/cm |
|---|-----------------------------------|----------|
| • | PET (covered side, initial)       | 7.8 N/cm |
| • | PP (initial)                      | 4.6 N/cm |
| • | PP (after 14 days)                | 4.4 N/cm |
| • | PP (covered side, after 14 days)  | 6.5 N/cm |
| • | PP (covered side, initial)        | 5.6 N/cm |
| • | PS (initial)                      | 5.8 N/cm |
| • | PS (after 14 days)                | 7.4 N/cm |
| • | PS (covered side, after 14 days)  | 8.2 N/cm |
| • | PS (covered side, initial)        | 8.1 N/cm |
| • | PVC (initial)                     | 4.8 N/cm |
| • | PVC (after 14 days)               | 7.7 N/cm |
| • | PVC (covered side, after 14       | 7.8 N/cm |
|   | days)                             |          |
| • | PVC (covered side, initial)       | 7.8 N/cm |
| • | Steel (initial)                   | 7 N/cm   |
| • | Steel (after 14 days)             | 7.8 N/cm |
| • | Steel (covered side, after 14     | 9.3 N/cm |
|   | days)                             |          |
| • | Steel (covered side, initial)     | 8.2 N/cm |
| • | Steel (covered side, initial)     | 8.2 N/cm |





**Product Information** 

## **Additional Information**

According to VDA278 analysis, tesa 4914 does not contain any single substances restricted by the drafted GB regulations (China) as well as the indoor concentration guideline by Health, Labour and Welfare Ministry (Japan).

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

