



8410 HS

Product Information

60µm/2.4 mils amber reactive HAF mounting tape



Product Description

tesa HAF® 8410 is a heat activated double-sided amber adhesive film based on reactive phenolic resin and nitrile rubber.

Special Features:

- Reliable chip module bonding
- Suitable for PVC, ABS, PET, and PC cards
- Good workability on all common implanting lines
- Outstanding ageing resistance
- Lifelong flexibility due to high rubber content

Product Features

- Reliable chip module bonding
- Suitable for PVC, ABS, PET, and PC cards
- Good workability on all common implanting lines
- Outstanding ageing resistance
- Lifelong flexibility due to high rubber content

Application Fields

tesa HAF® 8410 is especially designed for the embedding of chip-modules into smart cards. It is also suitable for bonding of all thermal resistant materials such as metal, glass, plastic, wood and textiles e.g. friction liners for clutches).

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|------------------------------------|-------------------|-------------------|
| • Backing | none | • Total thickness | 60 µm |
| • Type of adhesive | nitrile rubber /
phenolic resin | • Color | 2.4 mils
amber |
| • Type of liner | glassine | | |

Properties/Performance Values

- | | |
|------------------------------------|----------------------|
| • Bonding strength (dynamic shear) | 12 N/mm ² |
|------------------------------------|----------------------|

Additional Information

Technical recommendations for Smart Card applications:

For latest information on this product please visit <http://l.tesa.com/?ip=08410>



8410 HS

Product Information

Additional Information

tesa HAF® 8410 is not self adhesive. It is activated by heat and pressure over a certain interval. The following values are recommendations for machine parameters to start with. Please note that optimum parameters strongly depend on the type of machine, particular materials for card bodies and chip modules as well as customer requirements.

1. Pre-lamination:

During pre-lamination, the adhesive tape is laminated onto the module belt. The pre-lamination step does not affect the shelf life time of the adhesive tape. Pre-laminated belts can be stored over the same period of time as the adhesive tape.

Machine setting:

- Temperature 120 – 140 °C
- Pressure 2 – 3 bar
- Time 2.5 m/min

2. Module embedding:

During module embedding, the pre-laminated modules are cut from the module belt, positioned into the card cavity and permanently bonded to the card body by heat and pressure. Depending on the type of implanting line, single-step or multiple-step process are possible. Today, most implanting machines have multiple heat press steps.

Single-step process - machine setting:

- Temperature¹ 180 – 200 °C
- Pressure 65 – 75 N/module
- Time 1.5 s

Multiple-step process - machine setting:

- Temperature¹ 180 – 200 °C
- Pressure 65 – 75 N/module
- Time 2 x 0.7 s / 3 x 0.5 s

¹ Temperature measured inside the heating stamp. Different temperature settings recommended for different card materials:

PVC and ABS: 180 – 190 °C

PET and PC: 190 – 200 °C

Bonding strength values were obtained under standard laboratory conditions. Value is specification limit checked for each production batch (material: etched aluminum test specimen / bonding conditions: Temp. = 120 °C; pressure = 10 bar; time = 8 min).

To reach maximum bonding strength, surfaces should be clean and dry. Storage condition according to tesa HAF® shelf life concept.



8410

HS

Product Information

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=08410>