




tesa® 68942

Product Information



50µm double sided white filmic tape

Product Description

tesa® 68942 is a white, double-sided self-adhesive tape consisting of a white PET backing and a tackified acrylic adhesive.

Product Features

- Thickness: 50µm
- High adhesion level
- White color for easy detection or design purpose
- High resistance to demanding environmental conditions
- Good handling performance in converting processes

Application Fields

tesa® 68942 is used for general mounting and laminating applications especially in the electronics industry.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|-------------------|-------|
| • Backing | PET film | • Total thickness | 50 µm |
| • Type of adhesive | tackified acrylic | • Color | white |

Properties/Performance Values

- | | | | |
|--------------------------|-----------|-------------------------------------|--------|
| • Elongation at break | 50 % | • Static shear resistance at 23°C | medium |
| • Tensile strength | 20 N/cm | • Tack | good |
| • Ageing resistance (UV) | very good | • Temperature resistance long term | 100 °C |
| • Humidity resistance | very good | • Temperature resistance short term | 200 °C |
| • Softener resistance | very good | | |

Adhesion to Values

- | | | | |
|-----------------------------|----------|-------------------------|----------|
| • ABS (initial) | 5 N/cm | • PC (initial) | 5.3 N/cm |
| • ABS (after 14 days) | 6.1 N/cm | • PC (after 14 days) | 6.4 N/cm |
| • Aluminium (initial) | 5 N/cm | • Steel (initial) | 5.5 N/cm |
| • Aluminium (after 14 days) | 6 N/cm | • Steel (after 14 days) | 7.3 N/cm |

For latest information on this product please visit <http://l.tesa.com/?ip=68942>



tesa[®] 68942

Product Information

Additional Information

Liner variants:

PV20: brown/blue logo glassine paper (71µm; 82g/m²)

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=68942>