



Product Information

300µm double sided transparent filmic tape

Product Description

tesa® 68599 is a transparent double-sided self-adhesive tape consisting of a PET backing and a modified acrylic adhesive.

Product Features

- Thickness: 300µm
- High bonding strength
- High resistance to demanding environmental conditions
- Good handling performance in converting processes

Application Fields

tesa® 68599 is used for general mounting and lamination applications

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

BackingType of adhesiveType of linerTotal thickness	PET film modified acrylic glassine 300 μm	ColorColor of linerWeight of liner	transparent brown/blue logo 80 g/m²
Properties/Performance Values			
 Elongation at break Tensile strength Ageing resistance (UV) Humidity resistance 	50 % 30 N/cm very good very good	 Static shear resistance at 23°C Static shear resistance at 40°C Temperature resistance long term Temperature resistance short term 	good good 100 °C 200 °C
Adhesion to Values			
 PC (initial) PC (after 14 days) PE (initial) 	12.6 N/cm 14.3 N/cm 6 N/cm	PE (after 14 days)Steel (initial)Steel (after 14 days)	6.4 N/cm 13.8 N/cm 14.5 N/cm





Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 22/02/24 – en-US