



tesa[®] 4338

Product Information



Maskeringstape med høy vedheft opp til 120°C

Produktbeskrivelse

tesa[®] 4338 PV 1 er en grønnfarget glatt maskeringstape med sterk vedheft. Den anbefales til transportsektorer som skipsfart, tog, lastebil og diverse andre der det kreves sterk vedheft for å holde store og tunge maskeringer.

Sustainable Aspects

54% bio-based content in total product excluding liner (by weight)



For more information: <https://www.tesa.com/product-sustainability>

Funksjoner

- Det grønnfargede og glatte bærematerialet i papir sikrer fremragende synlighet, høy formbarhet og rene malingskanter
- Det aldri bestående klebemiddelet i naturgummi er svært hurtigklebende
- Tapen kan brukes utendørs i opptil syv dager
- Den gir temperaturbestandighet opp til 120°C / 248 F og ren fjerning.

Applikasjon

- Bærematerialet i papir er glatt og fingervennlig.
- Kan brukes i flere tørkesykluser (opptil 3 sykluser ved 120°C / 40 min.)
- Kan brukes i opptil 7 dager utendørs eller 30 dager innendørs
- Fjerning uten kleberester etter nedkjøling av underlag
- Bærematerialet har fremragende malingsvedheft
- Rivebestandig
- Fremragende formbarhet

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Produktinnhold

- | | | | |
|-----------------|---------------------|--|--------|
| • Bæremateriale | Papir (Lett kreppt) | • Total sustainable product excl. liners by weight (acc. EN 16785) | 54 % |
| • Klebetype | Naturgummi | • Total tykkelse | 145 µm |

For latest information on this product please visit <http://l.tesa.com/?ip=04338>



tesa[®] 4338

Product Information

Egenskaper / ytelsesverdier

- | | | | |
|--------------------|---------|--------------------|-----------|
| • Bruddforlengelse | 13 % | • Hand tearability | very good |
| • Bruddstyrke | 43 N/cm | • Lett å fjerne | Ja |

Klebekraft

- | | |
|---------------------|--------|
| • Klebeevne på Stål | 4 N/cm |
|---------------------|--------|

Additional Information

Fås også som tesa[®]4338 PV 0 med standard klebekraft.

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04338>