



tesa[®] 61895

SPT Series

Product Information

200µm d/s black Shock and Push-out Technology filmic tape

Product Description

tesa[®] 61895 is a double-sided self-adhesive tape consisting of a black PET backing equipped with a novel acrylic adhesive.

Product Features

- Very high bonding strength
- Outstanding push-out resistance
- Outstanding shock resistance
- Good LSE performance
- Excellent resistance to demanding environmental conditions
- Black color for easy detection or design purposes

Application Fields

- Cover lens mounting in electronic devices
- Touch panel mounting in electronic devices

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|------------------|----------------------|---------------------|
| • Backing | PET film | • Color | black |
| • Type of adhesive | modified acrylic | • Color of liner | transparent |
| • Type of liner | PET | • Thickness of liner | 50 µm |
| • Total thickness | 200 µm | • Weight of liner | 70 g/m ² |

Properties/Performance Values

- | | | | |
|-----------------------------------|-----------|-------------------------------------|--------|
| • Elongation at break | 50 % | • Static shear resistance at 40°C | good |
| • Tensile strength | 20 N/cm | • Tack | medium |
| • Ageing resistance (UV) | very good | • Temperature resistance long term | 100 °C |
| • Humidity resistance | very good | • Temperature resistance short term | 200 °C |
| • Static shear resistance at 23°C | good | | |

Adhesion to Values

- | | | | |
|----------------------|---------|-------------------------|---------|
| • PC (initial) | 14 N/cm | • Steel (initial) | 14 N/cm |
| • PC (after 14 days) | 17 N/cm | • Steel (after 14 days) | 15 N/cm |

For latest information on this product please visit <http://l.tesa.com/?ip=61895>



tesa[®] 61895 SPT Series

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=61895>