

# tesa® 66013 Ultra Low VOC

**Product Information** 



130  $\mu m$  reinforced water-based acrylic adhesive layer with PET scrim for mounting applications in automotive interiors

### **Product Description**

tesa® 66013 is a conformable, water-based acrylic adhesive tape with a thickness of 130 μm, reinforced by a PET scrim. This tape has especially been developed for all kinds of demanding lamination and mounting applications. Due to its low VOC property it is particularly designed to meet automotive interior requirements.

tesa® 66013 is suitable for laminating all kinds of foam, fleece, and felt substrates and mounting light interior components.

This product is also available in 75  $\mu m$ (tesa® 66007) and 220  $\mu m$  (tesa® 66022).

### **Product Features**

- Highly conformable to follow difficult 3-D shapes
- Low VOC (acc. GB 27630) no critical substances detectable
- Reinforcement supports converting efficiency
- Very low total VOC values
- High initial tack and peel adhesion
- Excellent initial adhesion to a wide variety of interior substrates
- Secure mounting even to nonpolar plastics (PP) and composites (recycled materials)

#### **Application Fields**

tesa® 66013 is suitable for various types of mounting and lamination applications.

Example applications are:

- Mounting of light interior trims (plastics, LSE surfaces)
- FPC (flexible printed circuits) mounting
- Lamination of insulation materials
- Laminates for NVH (noise, vibration, and harshness) and BSR (buzz, squeak, and rattle) prevention
- Lamination of decorative fabrics
- Lamination of foam for HVAC (heating, ventilation, and air conditioning) seals
- Mounting of flooring systems

To ensure the highest performance possible, our aim is to fully understand your application (including the substrates involved) in order to provide the right product recommendation.



# tesa® 66013 Ultra Low VOC

### **Product Information**

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

<ul><li>Backing material</li><li>Type of adhesive</li><li>Type of liner</li></ul>	none water-based acrylic glassine	<ul><li>Color</li><li>Color of liner</li><li>Thickness of liner</li></ul>	transparent brown/blue logo 71 μm		
Properties/Performance Values					
	very good	<ul> <li>Temperature resistance max</li> </ul>	180 °C		

<ul><li> Low VOC</li><li> Suitable for rough surfaces</li><li> Tack</li></ul>	very good very good very good	<ul> <li>Temperature resistance min.</li> </ul>	-40 °C
Adhesion to Values			
ABS (initial)	14.5 N/cm	• PP (initial)	8 N/cm
<ul> <li>ABS (after 3 days)</li> </ul>	14.5 N/cm	<ul> <li>PP (after 3 days)</li> </ul>	12 N/cm
PC (initial)	14.5 N/cm	<ul> <li>PS (initial)</li> </ul>	14.6 N/cm
<ul> <li>PC (after 3 days)</li> </ul>	15.1 N/cm	<ul> <li>PVC (initial)</li> </ul>	12 N/cm
PE (initial)	5.9 N/cm	Steel (initial)	15.4 N/cm

PE (initial)
PET (initial)
PET (after 3 days)
PET (after 3 days)

#### **Storage Conditions**

#### Storage Conditions

23°C, 50% RH, stored in original box

#### **Additional Information**

According to VDA278 analysis, our 66013-tapes does not contain any single substances restricted by the drafted GB regulations (China) as well as the indoor concentration guideline by Health, Labour and Welfare Ministry (Japan). Ultra low total VOC concentration according to VDA 278 analysis

Adhesion vaules to:	
PVC	
PP	
ABS	
PC	
PET	
PS	
PE	

16.5 N/cm

For latest information on this product please visit http://l.tesa.com/?ip=66013



# tesa® 66013 Ultra Low VOC

**Product Information** 

### **Additional Information**

Are not part of the product specification

PV20 brown glassine liner / blue tesa logo other liner version possible - on request

#### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 3 of 3 – as of 01/04/25 – en-SA