



Product Information



Double-sided film tape

Product Description

tesa® 64620 is a double-sided self-adhesive tape, consisting of a white PP-carrier and a synthetic rubber adhesive mass system (hotmelt). With the hotmelt adhesive, tesa® 64620 is solvent free and offers a high tack. tesa® 64620 is protected by a siliconized paper liner.

Product Features

- tesa® 64620 is protected by a siliconized paper liner.
- With the hotmelt adhesive, tesa® 64620 is solvent free and offers a high tack.

Applications

- Floor Laying
- General purpose fixing tape

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Applications

| BackingType of adhesiveType of linerTotal thickness | PP film synthetic rubber glassine 185 μm | ColorColor of linerThickness of linerWeight of liner | white brown 70 μm 78 g/m ² | | | | |
|--|---|---|--|--|--|--|--|
| Properties/Performance Values | | | | | | | |

| • | Elongation at break Tensile strength Ageing resistance (UV) Fogging Static shear resistance at 40°C | 700 % 30 N/cm low very good good, medium | • | Static shear resistance at 70°C Tack Temperature resistance long term Temperature resistance short term | medium, good very good 40 °C 80 °C | | |
|--------------------|---|--|---|--|---|--|--|
| Adhesion to Values | | | | | | | |

| • | PE (initial) | 5 N/cm • | PVC (after 14 days) | 10 N/cm |
|---|--------------------|-------------|-------------------------------|-----------|
| • | PE (after 14 days) | 8 N/cm • | Steel (initial) | 9.5 N/cm |
| • | PP (initial) | 8.5 N/cm • | Steel (after 14 days) | 14.5 N/cm |
| • | PP (after 14 days) | 12.5 N/cm • | Steel (covered side, initial) | 10.5 N/cm |
| ٠ | PVC (initial) | 7.5 N/cm | | |





Product Information

Additional Information

Suitable for plasticizer free flooring materials

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 17/02/24 – en-AU