

# tesa® 6917

## **Product Information**



Filmic double-sided bag sealing tape with differential adhesive

## **Product Description**

tesa® 6917 has been designed for re-sealable filmic bags. It consists of a transparent double-sided PP-film with a differential adhesive system. The product can easily be cut with the hot wire systems of common bag machine producers. Due to different adhesion values on each side, tesa® 6917 offers good removability on the covered adhesive side.

tesa® 6917 comes with fingerlift (extended liner) for conveniant liner removal.

## **Application Fields**

- Reopenable closure system for filmic bags
- · Removable emblems or profiles

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## **Applications**

•	Backing	PP film	•	Color	transparent
•	Type of adhesive	tackified acrylic	•	Color of liner	red
•	Type of liner	MOPP	•	Thickness of liner	80 μm
	Total thickness	90 um			

#### **Properties/Performance Values**

•	Elongation at break	150 %	•	Static shear resistance at 23°C	good
•	Ageing resistance (UV)	very good	•	Static shear resistance at 40°C	good
•	Chemical Resistance	good	•	Tack	good
•	Humidity resistance	very good	•	Temperature resistance long	80 °C
•	Softener resistance	medium		term	
			•	Temperature resistance short	120 °C
				term	



## tesa® 6917

## **Product Information**

#### Adhesion to Values

•	ABS (initial)	6.9 N/cm	•	PET (covered side, after 14 days)	4.7 N/cm
•	ABS (after 14 days)	10.1 N/cm	•	PET (covered side, initial)	3.1 N/cm
•	ABS (covered side, after 14	6 N/cm	•	PP (initial)	3.8 N/cm
	days)		•	PP (after 14 days)	6.9 N/cm
•	ABS (covered side, initial)	4.2 N/cm	•	PP (covered side, after 14 days)	2.6 N/cm
•	Aluminium (initial)	7.7 N/cm	•	PP (covered side, initial)	1.9 N/cm
•	Aluminium (after 14 days)	10.2 N/cm	•	PS (initial)	7.9 N/cm
•	Aluminium (covered side, after	4.7 N/cm	•	PS (after 14 days)	10 N/cm
	14 days)		•	PS (covered side, after 14 days)	5.6 N/cm
•	Aluminium (covered side, initial)	3.5 N/cm	•	PS (covered side, initial)	3.8 N/cm
•	PC (initial)	9 N/cm	•	PVC (initial)	6.5 N/cm
•	PC (after 14 days)	11 N/cm	•	PVC (after 14 days)	11 N/cm
•	PC (covered side, after 14 days)	6.8 N/cm	•	PVC (covered side, after 14	7 N/cm
•	PC (covered side, initial)	4 N/cm		days)	
•	PE (initial)	3.9 N/cm	•	PVC (covered side, initial)	4 N/cm
•	PE (after 14 days)	4.1 N/cm	•	Steel (initial)	8.2 N/cm
•	PE (covered side, after 14 days)	2.3 N/cm	•	Steel (after 14 days)	11.4 N/cm
•	PE (covered side, initial)	1.6 N/cm	•	Steel (covered side, after 14	4.1 N/cm
•	PET (initial)	6.6 N/cm		days)	
•	PET (after 14 days)	9.3 N/cm	•	Steel (covered side, initial)	4.5 N/cm

#### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

