



tesa® 62530

Product Information



Double sided PE-foam mounting tape

Product Description

tesa® 62530 is a double sided PE foam tape for general mounting applications. It consists of a highly conformable closed cell PE foam backing and a tackified acrylic adhesive. The foam tape features good adhesion on strongly structured surfaces as well as a high tack and a short dwell time until reaching final adhesion. tesa® 62530 is able to withstand humidity, chemicals, softeners and UV light. tesa® 62530 is a highly versatile adhesive, offering excellent immediate adhesion on numerous substrates, even at low bonding pressures. The double sided foam tape is fully suitable for outdoor use, featuring water-, ageing- and UV-resistance. The acrylic foam offers very good cold shock absorption, is capable of levelling out different thermal expansions and offers excellent bonding strength. Due to the foam's conformability, tesa® 62530 has a strong hold even on irregular or rough substrates.

Product Features

- Good adhesion on strongly structured surfaces
- Versatile adhesive for high immediate adhesion on numerous substrates
- Fully outdoor suitable: UV, water and ageing resistant
- High immediate adhesion even at low bonding pressure
- Very good cold shock absorption

Applications

- tesa® 62530 is used for demanding long-term constructive applications, including:
 - Window skirting trims
 - Muntin bars
 - Dust and moisture seals
 - Decorative elements on doors
- The foam tape is available with other liner variants
- tesa® 62530 is available in various thicknesses: 500 µm, 800µm, 1,600 µm, 2,000 µm and 3,000 µm

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Applications

- | | | | |
|--------------------|-------------------|-------------------|-------------|
| • Backing | PE foam | • Total thickness | 3000 µm |
| • Type of adhesive | tackified acrylic | • Color | black/white |



tesa[®] 62530

Product Information

Properties/Performance Values

• Elongation at break	160 %	• Static shear resistance at 23°C	good
• Tensile strength	13.3 N/cm	• Static shear resistance at 40°C	good
• Ageing resistance (UV)	good	• Tack	good
• Batteries required	no	• Temperature resistance long term	80 °C
• Chemical Resistance	very good	• Temperature resistance short term	80 °C
• Humidity resistance	very good	• Tensibility	140 %
• Softener resistance	medium		

Adhesion to Values

• ABS (initial)	6 N/cm	• PET (after 14 days)	6 N/cm
• ABS (after 14 days)	6 N/cm	• PP (initial)	6 N/cm
• Aluminium (initial)	6 N/cm	• PP (after 14 days)	6 N/cm
• Aluminium (after 14 days)	6 N/cm	• PS (initial)	6 N/cm
• PC (initial)	6 N/cm	• PS (after 14 days)	6 N/cm
• PC (after 14 days)	6 N/cm	• PVC (initial)	6 N/cm
• PE (initial)	2 N/cm	• PVC (after 14 days)	6 N/cm
• PE (after 14 days)	2 N/cm	• Steel (initial)	6 N/cm
• PET (initial)	6 N/cm	• Steel (after 14 days)	6 N/cm

Additional Information

Peel Adhesion:

- Immediate and after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC

Longterm dampening properties and temperature resistance have been certified by ift institute, Germany (Report no. 105 32948/1)

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=62530>