



tesa[®] 4926

Product Information

250µm double sided transparent filmic tape

Product Description

tesa[®] 4926 is a transparent, double-sided self-adhesive tape consisting of a 50µm PET film backing and a tackified acrylic adhesive.

Special features:

- Thickness: 250µm
- Very high bonding strength and shear resistance
- Superior handling and processing performance due to very strong PET backing
- Very good dimensional stability
- Excellent resistance to demanding environmental conditions

Product Features

- Thickness: 250µm
- Very high bonding strength and shear resistance
- Superior handling and processing performance due to very strong PET backing
- Very good dimensional stability
- Excellent resistance to demanding environmental conditions

Applications

- Lens mounting in mobile phones
- Antenna mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Applications

• Backing	PET film	• Color	transparent
• Type of adhesive	tackified acrylic	• Color of liner	brown
• Type of liner	glassine	• Thickness of liner	71 µm
• Total thickness	250 µm	• Weight of liner	82 g/m ²



tesa[®] 4926

Product Information

Properties/Performance Values

• Elongation at break	60 %	• Static shear resistance at 23°C	good
• Tensile strength	73 N/cm	• Static shear resistance at 40°C	good
• Ageing resistance (UV)	very good	• Tack	good
• Chemical Resistance	good	• Temperature resistance long term	100 °C
• Humidity resistance	very good	• Temperature resistance short term	200 °C
• Softener resistance	good		

Adhesion to Values

• ABS (initial)	11.8 N/cm	• PE (initial)	5.1 N/cm
• ABS (after 14 days)	14.1 N/cm	• PE (after 14 days)	7.5 N/cm
• PC (initial)	14.6 N/cm	• Steel (initial)	13.8 N/cm
• PC (after 14 days)	17 N/cm	• Steel (after 14 days)	16.2 N/cm

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04926>