



tesa® 4985

Product Information



Tacky transfer tape

Product Description

tesa® 4985 is a transparent transfer tape using a modified acrylic adhesive. It offers good immediate hold to uneven surfaces and is very tacky. The transfer tape is extremely thin and flexible and thus very conformable. The acrylic adhesive features high resistance to UV light and humidity as well as a good resistance against chemicals and softeners. tesa® 4985 can withstand temperatures of up to 200°C for short periods of time and has a long-term resistance against temperatures of up to 80°C. The tape is highly cost-efficient and can be used for a range of different mounting and splicing applications.

Product Features

- Excellent conformability due to transfer tape construction
- Good dispensing properties
- It offers good immediate grab to uneven surfaces.

Applications

- tesa® 4985 is a highly flexible and conformable transfer tape that is ideal for various mounting and splicing applications
- The transfer tape is used for mounting posters and photos
- The tape is ideal for mounting fabric for pattern books
- tesa® 4985 is used for splicing paper

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Applications

• Backing	none	• Color of liner	brown
• Type of adhesive	tackified acrylic	• Thickness of liner	71 µm
• Type of liner	glassine	• Weight of liner	80 g/m ²
• Total thickness	50 µm		

Properties/Performance Values

• Ageing resistance (UV)	very good	• Static shear resistance at 40°C	low
• Chemical Resistance	good	• Tack	very good
• Humidity resistance	very good	• Temperature resistance long term	80 °C
• Softener resistance	good	• Temperature resistance short term	200 °C
• Static shear resistance at 23°C	medium		



tesa® 4985

Product Information

Adhesion to Values

• ABS (initial)	6.9 N/cm	• PET (after 14 days)	6.4 N/cm
• ABS (after 14 days)	9.3 N/cm	• PP (initial)	3.5 N/cm
• Aluminium (initial)	7.1 N/cm	• PP (after 14 days)	5.7 N/cm
• Aluminium (after 14 days)	10 N/cm	• PS (initial)	7.2 N/cm
• PC (initial)	7.6 N/cm	• PS (after 14 days)	9.5 N/cm
• PC (after 14 days)	9.7 N/cm	• PVC (initial)	6.8 N/cm
• PE (initial)	4.1 N/cm	• PVC (after 14 days)	9.4 N/cm
• PE (after 14 days)	4.9 N/cm	• Steel (initial)	8 N/cm
• PET (initial)	4.9 N/cm	• Steel (after 14 days)	11.1 N/cm

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04985>