



## **Product Information**



## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## **Product Construction**

<ul> <li>Backing</li> <li>Type of adhesive</li> <li>Type of liner</li> <li>Total thickness</li> </ul> Properties/Performance Value	non-woven tackified acrylic PE-coated paper 120 μm	<ul><li>Color</li><li>Color of liner</li><li>Thickness of liner</li></ul>	translucent white/blue logo 130 μm
-			
<ul><li>Static shear resistance at 70°C</li><li>Tack</li></ul>	very good good	<ul> <li>Temperature resistance long term</li> </ul>	70 °C
		Temperature resistance short term	160 °C
Adhesion to Values			
<ul> <li>ABS (initial)</li> </ul>	8.5 N/cm	<ul> <li>PE (after 3 days)</li> </ul>	5 N/cm
ABS (after 3 days)	10.2 N/cm	PET (initial)	6.7 N/cm
Glass (initial)	7.5 N/cm	• PP (initial)	5.8 N/cm
<ul> <li>Glass (after 3 days)</li> </ul>	9.5 N/cm	<ul> <li>PP (after 3 days)</li> </ul>	7 N/cm
PC (initial)	9.1 N/cm	PVC (initial)	6.5 N/cm
<ul> <li>PC (after 3 days)</li> </ul>	11.7 N/cm	Steel (initial)	7.5 N/cm
• PE (initial)	4.4 N/cm	<ul> <li>Steel (after 3 days)</li> </ul>	10.1 N/cm

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.