



tesa® 4621

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	PE extruded cloth	• Total thickness	125 µm
• Type of adhesive	acrylic		

Properties/Performance Values

• Elongation at break	22 %	• Residue-free removability	yes
• Tensile strength	54 N/cm	• Straight tear edge	good
• Abrasion resistance	medium	• Tack	very good
• Ageing resistance (UV)	very good	• Temperature resistance	95 °C
• Easy to write on	yes	(removability from aluminum after 30 min exposure)	
• Hand tearability	very good	• UV-resistance	8 weeks
• Mesh	100 threads/inch ²	• Water resistance	good

Adhesion to Values

• Glass (initial)	2.7 N/cm	• Steel	2.6 N/cm
• PE (initial)	1.1 N/cm		

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04621>