

# tesa® 51970

## Product Information



220µm double sided transparent PP film tape

## Product Description

tesa® 51970 is a transparent, double-sided industrial mounting tape with a highly tackified adhesive and PP backing. The double-sided PP film tape is used in various different industries, frequently for mounting plastic or wooden trims or fastening signs and point-of-sale displays. The tackified acrylic adhesive features excellent adhesive performance, offering a reliable bond, often also on low energy surfaces and rough or slightly dirty substrates. tesa® 51970 is able to withstand numerous environmental factors such as humidity, UV light, and temperatures of up to 130°C for limited periods of time. The tackified acrylic adhesive offers excellent hold on various surfaces, very high tack, and good shear strength.

## Sustainable Aspects

tesa® More Sustainable Paper Liner:

- Responsibly sourced paper liner (certified)
- Unbleached paper with 30% recycled fibers



For more information: <https://www.tesa.com/product-sustainability>

## Product Features

- Excellent combination of high initial tack and immediate adhesion
- Light- and aging-resistant acrylic adhesive for long-term applications
- Reliable bond, often also on low surface energy surfaces

## Application Fields

- tesa® 51970 is suitable for various types of mounting applications
- Mounting plastic and wooden trims
- Ideal for mounting transparent signs and scales
- Mounting decorative materials and displays

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## Product Construction

• Backing material	PP film	• Total thickness	220 µm
• Type of adhesive	tackified acrylic	• Colour	transparent

For latest information on this product please visit <http://l.tesa.com/?ip=51970>

# tesa® 51970

## Product Information

### Properties/Performance Values

• Elongation at break	150 %	• Softener resistance	good
• Tensile strength	50 N/cm	• Static shear resistance at 23°C	good
• Ageing resistance (UV)	good	• Static shear resistance at 40°C	good
• Chemical resistance	good	• Tack	very good
• Humidity resistance	very good	• Temperature resistance long term duration	80 °C
• Minimum temperature resistance	-40 °C	• Temperature resistance short term duration	130 °C

### Adhesion to Values

• ABS (initial)	12.5 N/cm	• PET (after 14 days)	11.5 N/cm
• ABS (after 14 days)	14.5 N/cm	• PP (initial)	8.5 N/cm
• Aluminium (initial)	11.5 N/cm	• PP (after 14 days)	10 N/cm
• Aluminium (after 14 days)	12.5 N/cm	• PS (initial)	13 N/cm
• PC (initial)	15 N/cm	• PS (after 14 days)	14.5 N/cm
• PC (after 14 days)	16.5 N/cm	• PVC (initial)	11.5 N/cm
• PE (initial)	7 N/cm	• PVC (after 14 days)	17.5 N/cm
• PE (after 14 days)	8 N/cm	• Steel (initial)	13 N/cm
• PET (initial)	11 N/cm	• Steel (after 14 days)	13.5 N/cm

### Additional Information

Liner variants:

- PV0: brown glassine paper (69 µm; 80g/m<sup>2</sup>)
- PV1: white glassine paper (84 µm; 102g/m<sup>2</sup>)
- PV2: brown glassine paper (78µm; 90g/m<sup>2</sup>)
- PV6: red MOPP film (80 µm; 72g/m<sup>2</sup>)
- PV8: white MOPP friction liner (69 µm; 80g/m<sup>2</sup>)
- Sustainability Marker valid for paper liner version

For spools, it is recommended to use tesa® dispensers to achieve optimal results.

According to VDA278 analysis, tesa® 51970 does not contain any single substances restricted by the drafted GB regulations (China) as well as the indoor concentration guideline by Health, Labour and Welfare Ministry (Japan).

# tesa® 51970

## Product Information

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=51970>