




tesa® 61054

Product Information



250µm d/s black flexible acrylic foam tape

Product Description

tesa® 61054 is a double-sided black tape consisting of a high shock absorbing black acrylic foam.

Product Features

- Thickness: 250 µm
- Very high shock performance
- Very high thermal and cold shock resistance
- Very high bonding strength for wide temperature range
- Good anti-repulsion properties to prevent lifting
- Waterproofing
- Light blocking

Application Fields

- Display or touch panel mounting for electronic devices and infotainment systems
- Compensation of mechanical stress (e.g. gap filling and thermal elongation)
- Mounting of waterproof designs

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|------------------|----------------------|----------------------|
| • Backing material | Acrylic | • Colour | black |
| • Type of adhesive | modified acrylic | • Colour of liner | transparent |
| • Type of liner | PET | • Thickness of liner | 75 µm |
| • Total thickness | 250 µm | • Weight of liner | 105 g/m ² |

Product Assortment

- | | |
|-------------------------|--------------------|
| • Available thicknesses | 200, 250, 300, 400 |
|-------------------------|--------------------|

Properties/Performance Values

- | | | | |
|-----------------------------------|-----------|--|--------|
| • Ageing resistance (UV) | very good | • Temperature resistance long term duration | 90 °C |
| • Static shear resistance at 40°C | very good | • Temperature resistance short term duration | 180 °C |



tesa[®] 61054

Product Information

Adhesion to Values

• Aluminium (initial)	8.5 N/cm	• PC (initial)	14 N/cm
• Aluminium (after 3 days)	15.5 N/cm	• PC (after 3 days)	28.7 N/cm
• Glass (initial)	17 N/cm	• Steel (initial)	16 N/cm
• Glass (after 3 days)	18.5 N/cm	• Steel (after 3 days)	19 N/cm

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=61054>