



tesa® 4968

Product Information



Double-sided filmic tape

Product Description

tesa® 4968 is a white double-sided self-adhesive tape consisting of a PVC-backing and a tackified acrylic adhesive.

tesa® 4968 features especially:

- An outstanding adhesion level even to critical low surface energy materials such as PP and PE
- Immediate functionality of the laminated bond due to excellent initial tack
- A light and age-resistant acrylic adhesive

Application Fields

- Mounting of non-heated exterior car mirrors onto the holding plate
- Mounting of mouldings and decorative trim parts in the furniture industry

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing material	PVC film	• Colour	white
• Type of adhesive	tackified acrylic	• Colour of liner	brown
• Type of liner	paper	• Thickness of liner	69 µm
• Total thickness	295 µm	• Weight of liner	80 g/m ²

Properties/Performance Values

• Elongation at break	130 %	• Static shear resistance at 23°C	good
• Tensile strength	30 N/cm	• Static shear resistance at 40°C	medium
• Ageing resistance (UV)	good	• Tack	very good
• Chemical resistance	good	• Temperature resistance long term duration	60 °C
• Humidity resistance	very good	• Temperature resistance min.	-40 °C
• Softener resistance	very good	• Temperature resistance short term duration	70 °C



tesa® 4968

Product Information

Adhesion to Values

• ABS (initial)	13.1 N/cm	• PP (initial)	11 N/cm
• ABS (after 14 days)	20 N/cm	• PP (after 14 days)	14.1 N/cm
• Aluminium (initial)	10.3 N/cm	• PS (initial)	11.9 N/cm
• Aluminium (after 14 days)	20.7 N/cm	• PS (after 14 days)	18.2 N/cm
• PC (initial)	13.8 N/cm	• PVC (initial)	10.6 N/cm
• PC (after 14 days)	24.6 N/cm	• PVC (after 14 days)	25.3 N/cm
• PET (initial)	9.6 N/cm	• Steel (initial)	12.5 N/cm
• PET (after 14 days)	12.7 N/cm	• Steel (after 14 days)	21.2 N/cm

Additional Information

Liner variants:

PV0 brown glassine paper (71 µm)

PV4 white PE-coated paper (122 µm)

PV6 red MOPP-film (80 µm)

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04968>