



tesa® 64993

Product Information



Double-sided filmic tape

Product Description

tesa® 64993 is a white double-sided self-adhesive tape consisting of a PP-film backing and a tackified acrylic adhesive.

Product Features

- An excellent combination of a high initial tack and adhesion level
- A secure bond even on critical materials (such as PP and PE) and rough surfaces
- A good temperature resistance

Application Fields

- Mounting of exterior non-heated car mirrors onto the holding plate
- Mounting of heating elements of car mirrors onto the holding plate

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|-------------------------|---------|-------------------|--------|
| • Backing material Grid | PP film | • Total thickness | 240 µm |
| • Type of adhesive Grid | acrylic | • Colour | white |

Properties/Performance Values

- | | | | |
|--------------------------|--------------|--|--------------|
| • Elongation at break | 20 % | • Softener resistance | good, medium |
| • Tensile strength | 130 N/cm | • Static shear resistance at 23°C | good, medium |
| • Ageing resistance (UV) | good, medium | • Static shear resistance at 40°C | medium |
| • Chemical resistance | good, medium | • Tack | good, medium |
| • Humidity resistance | very good | • Temperature resistance short term duration | 120 °C |

Adhesion to Values

- | | | | |
|-----------------------|-----------|-----------------------|-----------|
| • ABS (initial) | 12 N/cm | • PET (initial) | 10 N/cm |
| • ABS (after 14 days) | 13.5 N/cm | • PET (after 14 days) | 10.5 N/cm |
| • PC (initial) | 14.5 N/cm | • PP (initial) | 8 N/cm |
| • PC (after 14 days) | 15.5 N/cm | • PP (after 14 days) | 9.5 N/cm |



tesa[®] 64993

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=64993>