

# tesa® ACXplus 7072 High Resistance

## **Product Information**

ACX<sup>plus</sup> High Resistance 500μm

# **Product Description**

tesa® ACX<sup>plus</sup> 7072 is a black acrylic foam tape. It consists of a high-performance acrylic system and due to its unique components it combines a very good temperature resistance with an outstanding cold shock resistance up to -40°C. It is designed for demanding outdoor bonding applications especially in combination with the tesa Adhesion Promoters. The visco-elastic, foamed acrylic core compensates different thermal elongation of bonded parts.

## **Product Features**

- Outstanding cold shock performance down to -40 °C
- · In combination with out adhesion promoters a secure and reliable bond in outdoor conditions

## **Application Fields**

Main Application: Bonding of panels and reinforcement bars in the following Industries:

- Elevator
- Transportation
- · Production equipment

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

•	Backing material	foamed acrylic	•	Total thickness	500 μm
•	Type of adhesive	pure acrylic	•	Colour	black

## **Properties/Performance Values**

•	Temperature resistance long	120 °C	<ul> <li>Temperature resistance short 220 °C</li> </ul>
	term duration		term duration

#### Adhesion to Values

•	ABS (initial)	2 N/cm	•	Steel (initial)	12 N/cm
•	ABS (after 14 days)	3 N/cm	•	Steel (after 14 days)	27 N/cm
•	PP (initial)	1 N/cm	•	Steel (after 3 days)	27 N/cm
•	PP (after 14 days)	1 N/cm			

#### **Additional Information**

PV 22 = White PE coated paper liner tesa® ACX<sup>plus</sup> branded

Page 1 of 2 – as of 18/06/25 – en-GB



# tesa® ACXplus 7072 High Resistance

**Product Information** 

## **Additional Information**

PV 24 = Blue filmic liner

tesa® ACX<sup>plus</sup> 7072 is recognized according to UL Standard 746C. UL File QOQW2.E309290

## Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

