

# tesa® 4983

## **Product Information**

## Double-sided ultrathin tape

# **Product Description**

tesa® 4983 is a transparent double-sided self-adhesive tape consisting of a PET backing and a tackified acrylic adhesive.

#### tesa® 4983 features:

- Low thickness of 30μm
- Good adhesion level relative to low thickness to smooth surfaces
- · Excellent resistance to demanding environmental conditions
- · Excellent handling performance in converting processes
- Dielectric bus bar mounting in thin film solar modules

#### **Product Features**

- Certified according to IEC 60454-3-1 (VDE, IMQ, SEMKO), VOC-certified, RoHS 2.0 and REACH conform
- Thickness: 30μm
- · Good adhesion level
- · Excellent resistance to demanding environmental conditions
- · Excellent handling performance in converting processes

# **Application Fields**

- · Lamination of cushioning materials to LCDs
- · Fixing of reflection foil to LCD frame
- Splicing of thin plastic films

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

٠	Backing material	PET film	•	Total thickness	30 μm
•	Type of adhesive	tackified acrylic	•	Colour	transparent



# tesa® 4983

## **Product Information**

## **Properties/Performance Values**

•	Elongation at break	50 %	•	Static shear resistance at 23°C
•	Tensile strength	20 N/cm	•	Static shear resistance at 40°C
•	Ageing resistance (UV)	very good	•	Tack
•	Chemical resistance	good	•	Temperature resistance long
•	Humidity resistance	very good		term duration
•	Softener resistance	good	•	Temperature resistance short
				term duration

#### Adhesion to Values

•	ABS (initial)	4.5 N/cm	•	PET (after 14 days)	4.8 N/cm
•	ABS (after 14 days)	5.3 N/cm	•	PP (initial)	2.3 N/cm
•	Aluminium (initial)	4.1 N/cm	•	PP (after 14 days)	3.7 N/cm
•	Aluminium (after 14 days)	5.5 N/cm	•	PS (initial)	4 N/cm
•	PC (initial)	5.2 N/cm	•	PS (after 14 days)	5.2 N/cm
•	PC (after 14 days)	6 N/cm	•	PVC (initial)	3.6 N/cm
•	PE (initial)	2 N/cm	•	PVC (after 14 days)	6.4 N/cm
•	PE (after 14 days)	3.3 N/cm	•	Steel (initial)	5.2 N/cm
•	PET (initial)	4.2 N/cm	•	Steel (after 14 days)	7.6 N/cm

### **Additional Information**

Recognized according to UL 969, file number MH18055

Liner variants:

PV0 brown glassine paper (71 $\mu$ m; 82g/m²) PV6 red MOPP-film (80 $\mu$ m; 72g/m²)

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



good medium low 100 °C

200°C