



tesa® ACXplus 79015

Product Information



1.5 mm double-sided acrylic foam tape for mounting of automotive exterior attachment part

Product Features

Good performance on LSE plastics and difficult-to-bond clear coats without primer

- Excellent bonding stability with long term temperature resistance up to 95°C
- PFAS / PFOS free Product
- Efficient and robust application
- Viscoelastic acrylic foam core to compensate for different thermal elongation of bonded parts
- Good wet-out property
- High humidity and UV resistance

LSE: low surface energy

MSE: medium surface energy

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|---------|-------------------|---------|
| • Backing material | Acrylic | • Total thickness | 1500 µm |
| • Type of adhesive | LSE | • Colour | gray |
| • Type of liner | PE | • Colour of liner | blue |

Properties/Performance Values

- | | | | |
|--------------------------|-----------|-----------------------------------|-----------|
| • Ageing resistance (UV) | good | • Humidity resistance | very good |
| • Chemical resistance | good | • Static shear resistance at 90°C | very good |
| • Cold-shock resistance | very good | • Temperature range | -40 to 95 |

Adhesion to Values

- | | | | |
|----------------------|---------|------------------------|---------|
| • ABS (initial) | 45 N/cm | • Steel (initial) | 35 N/cm |
| • ABS (after 3 days) | 45 N/cm | • Steel (after 3 days) | 35 N/cm |



tesa® ACXplus 79015

Product Information

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=79015>