



## **Product Information**



## **Sustainable Aspects**

Ì

For more information: https://www.tesa.com/product-sustainability

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## **Product Construction**

<ul> <li>Backing</li> <li>Type of adhesive</li> <li>Bio-based carbon content of liner (acc. ASTM D6866)</li> <li>Type of liner</li> <li>Post-consumer recycled content of liner</li> </ul>	none modified acrylic 66 % PET 88 %	<ul> <li>Total thickness</li> <li>Color</li> <li>Color of liner</li> <li>Thickness of liner</li> </ul>	100 μm black transparent 50 μm
Product Assortment			
Available thicknesses	100µm, 150µm, 200µm		
Properties/Performance Values			
Ageing resistance (UV)	very good		
Adhesion to Values			
<ul><li>Aluminium (initial)</li><li>Aluminium (after 3 days)</li></ul>	7 N/cm 7.5 N/cm	<ul><li>PC (after 3 days)</li><li>Steel (initial)</li></ul>	11 N/cm 8.5 N/cm

• Steel (after 3 days)

PC (initial)

Page 1 of 2 – as of 05/05/25 – en-IN

9 N/cm

10 N/cm





**Product Information** 

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 05/05/25 – en-IN