



tesa® 61526

Product Information

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	PETP	• Type of adhesive (easy release)	silicone
• Total thickness	30 µm	• Type of adhesive (tight release)	modified acrylic
• Color	transparent	• Type of liner (easy release)	PET
• Color of liner (tight release)	transparent	• Color of liner (easy release)	white
• Thickness of easy release liner	50 µm	• Type of liner (tight release)	PET
• Thickness of tight release liner	50 µm		

Properties/Performance Values

• Ageing resistance (UV)	very good	• Static shear resistance at 40°C	medium
• Humidity resistance	good	• Tack	very good
• Static shear resistance at 23°C	good		

Adhesion to Values

• PC (tight-side, initial)	8.9 N/cm	• Steel (easy-side, after 14 days)	4.7 N/cm
• PP (easy-side, after 14 days)	4.5 N/cm	• Steel (easy-side, initial)	4 N/cm
• PP (easy-side, initial)	4.2 N/cm	• Steel (tight-side, after 14 days)	7.7 N/cm
• Silicone (easy-side, after 14 days)	4.5 N/cm	• Steel (tight-side, initial)	6.8 N/cm
• Silicone (easy-side, initial)	3 N/cm		

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.