




tesa® 75620

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	Acrylic	• Color	black
• Type of adhesive	modified acrylic	• Color of liner	transparent
• Type of liner	PET	• Thickness of liner	75 µm
• Total thickness	200 µm	• Weight of liner	105 g/m ²

Properties/Performance Values

• Ageing resistance (UV)	very good	• Temperature resistance long term	90 °C
• Static shear resistance at 40°C	very good	• Temperature resistance short term	180 °C

Adhesion to Values

• Aluminium (initial)	8.5 N/cm	• PC (initial)	13.5 N/cm
• Aluminium (after 3 days)	14.5 N/cm	• PC (after 3 days)	26.5 N/cm
• Glass (initial)	13.5 N/cm	• Steel (initial)	15.5 N/cm
• Glass (after 3 days)	15.5 N/cm	• Steel (after 3 days)	17 N/cm

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=75620>