




tesa® 64815

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	stretchable specialty	• Total thickness	150 µm
• Type of adhesive	synthetic rubber	• Color	white
• Type of liner	PET	• Color of liner	transparent

Properties/Performance Values

• Removability after 14 days (23°C)	very good	• Static shear resistance at 40°C	very good
• Residue-free removability	yes	• Temperature resistance long term	60 °C
• Static shear resistance at 23°C	very good	• Temperature resistance short term	90 °C

Adhesion to Values

• Aluminium (initial)	10 N/cm	• PE (initial)	10 N/cm
• Aluminium (after 14 days)	10 N/cm	• PE (after 14 days)	10 N/cm
• Magnesium (initial)	10 N/cm	• Steel (initial)	12 N/cm
• Magnesium (after 14 days)	10 N/cm	• Steel (after 14 days)	12 N/cm

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.