




# tesa® 76020

## Product Information



## Sustainable Aspects



For more information: <https://www.tesa.com/product-sustainability>

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

• Backing	none	• Post-consumer recycled content of liner	88 %
• Type of adhesive	modified acrylic	• Total thickness	200 µm
• Bio-based carbon content of liner (acc. ASTM D6866)	66 %	• Color	black
• Type of liner	PET	• Color of liner	transparent
• Bio-based carbon content of liner (acc. ASTM D6866)	66 %	• Thickness of liner	50 µm

### Product Assortment

• Available thicknesses	100µm, 150µm, 200µm
-------------------------	---------------------

### Properties/Performance Values

• Ageing resistance (UV)	very good
--------------------------	-----------

### Adhesion to Values

• Aluminium (initial)	8.5 N/cm	• PC (after 3 days)	13 N/cm
• Aluminium (after 3 days)	10 N/cm	• Steel (initial)	11 N/cm
• PC (initial)	12 N/cm	• Steel (after 3 days)	12 N/cm



# tesa® 76020

## Product Information

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=76020>