



tesa® 51926

Product Information

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	PET film	• Color	black
• Type of adhesive	tackified acrylic	• Color of liner	brown
• Type of liner	glassine	• Thickness of liner	71 µm
• Total thickness	250 µm	• Weight of liner	82 g/m ²

Properties/Performance Values

• Elongation at break	60 %	• Static shear resistance at 23°C	good
• Tensile strength	73 N/cm	• Static shear resistance at 40°C	good
• Ageing resistance (UV)	very good	• Tack	good
• Chemical Resistance	good	• Temperature resistance long term	100 °C
• Humidity resistance	very good	• Temperature resistance short term	200 °C
• Softener resistance	good		

Adhesion to Values

• ABS (initial)	11.8 N/cm	• PE (initial)	5.1 N/cm
• ABS (after 14 days)	14.1 N/cm	• PE (after 14 days)	7.5 N/cm
• PC (initial)	14.6 N/cm	• Steel (initial)	13.8 N/cm
• PC (after 14 days)	17 N/cm	• Steel (after 14 days)	16.2 N/cm

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.