



# tesa® 77711

## Product Information



## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

• Backing	Acrylic foam	• Total thickness	1100 µm
• Type of adhesive	LSE	• Color	gray
• Type of liner	PE	• Color of liner	blue

### Properties/Performance Values

• Ageing resistance (UV)	good	• Static shear resistance at 90°C	very good
• Humidity resistance	very good	• T-block	very good
• L-jig	good	• Temperature range	-40 to +80°C

### Adhesion to Values

• ABS (after 3 days)	28 N/cm	• PP (initial, 1 min)	24 N/cm
• ABS (covered side, after 3 days)	12 N/cm	• Steel (after 3 days)	31 N/cm
• ABS (covered side, initial)	8 N/cm	• Steel (covered side, after 3 days)	26 N/cm
• ABS (initial, after 1 minute)	23 N/cm	• Steel (covered side, initial)	12 N/cm
• PP (after 3 days)	30 N/cm	• Steel (initial, 1 min)	25 N/cm

## Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=77711>