



tesa® 75515

Product Information



Sustainable Aspects



For more information: <https://www.tesa.com/product-sustainability>

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-------------------|----------------------|---------------------|
| • Backing | none | • Color of liner | brown/blue logo |
| • Type of adhesive | tackified acrylic | • Thickness of liner | 70 µm |
| • Type of liner | glassine | • Weight of liner | 80 g/m ² |
| • Color | transparent | | |

Properties/Performance Values

- | | | | |
|-----------------------------------|-----------|-------------------------------------|-----------|
| • Ageing resistance (UV) | good | • Static shear resistance at 40°C | very good |
| • Chemical Resistance | good | • Tack | good |
| • Humidity resistance | very good | • Temperature resistance long term | 100 °C |
| • Softener resistance | good | • Temperature resistance min. | -40 °C |
| • Static shear resistance at 23°C | very good | • Temperature resistance short term | 200 °C |

Adhesion to Values

- | | | | |
|-----------------------------|-----------|-------------------------|----------|
| • ABS (initial) | 11 N/cm | • PP (initial) | 5 N/cm |
| • ABS (after 14 days) | 13 N/cm | • PP (after 14 days) | 6.5 N/cm |
| • Aluminium (initial) | 10 N/cm | • PS (initial) | 12 N/cm |
| • Aluminium (after 14 days) | 11 N/cm | • PS (after 14 days) | 13 N/cm |
| • PC (initial) | 14 N/cm | • PVC (initial) | 9 N/cm |
| • PC (after 14 days) | 14.5 N/cm | • PVC (after 14 days) | 15 N/cm |
| • PE (initial) | 5 N/cm | • Steel (initial) | 14 N/cm |
| • PE (after 14 days) | 6 N/cm | • Steel (after 14 days) | 12 N/cm |
| • PET (initial) | 10 N/cm | • Steel (after 3 days) | 14 N/cm |
| • PET (after 14 days) | 10 N/cm | | |

For latest information on this product please visit <http://l.tesa.com/?ip=75515>



tesa[®] 75515

Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=75515>