

tesa® 58346

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	PET film	• Total thickness	90 µm
• Type of adhesive	tackified acrylic	• Color	transparent
• Type of liner	PET film	• Thickness of liner	36 µm

Properties/Performance Values

• Elongation at break	140 %	• Humidity resistance	very good
• Chemical Resistance	medium	• Suitable for die cutting	yes
• Dielectric breakdown voltage	12000 V	• Temperature resistance long term	125 °C
• Easy to remove	yes		

Adhesion to Values

• Aluminium (initial)	0.16 N/cm	• Steel (initial)	0.22 N/cm
-----------------------	-----------	-------------------	-----------

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=58346>