


tesa® 70615

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	none	• Color	black
• Type of adhesive	specialty	• Color of liner	brown
• Type of liner	glassine	• Thickness of liner	72 µm
• Total thickness	150 µm		

Properties/Performance Values

• Ageing resistance (UV)	good	• Static shear resistance at 23°C	very good
• Humidity resistance	good	• Static shear resistance at 40°C	very good
• Removability after 14 days (23°C)	very good	• Temperature resistance long term	60 °C
• Residue-free removability	yes	• Temperature resistance short term	90 °C
• Solvent free	yes		

Adhesion to Values

• Aluminium (initial)	10 N/cm	• PE (initial)	7 N/cm
• Aluminium (after 14 days)	10 N/cm	• PE (after 14 days)	7 N/cm
• Magnesium (initial)	8 N/cm	• Steel (initial)	13 N/cm
• Magnesium (after 14 days)	8 N/cm	• Steel (after 14 days)	13 N/cm

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=70615>