

tesa® 88676

Product Information



Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Type of adhesive	tackified acrylic	• Color	transparent
• Type of liner	PE-coated paper	• Color of liner	white/blue logo
• Total thickness	170 µm	• Thickness of liner	140 µm

Product Assortment

• Available liners	PE-coated paper
--------------------	-----------------

Properties/Performance Values

• Elongation at break	98 %	• Static shear resistance at 40°C	good
• Tensile strength	30.2 N/cm	• Tack	very good
• Ageing resistance (UV)	good	• Temperature resistance long term	95 °C
• Static shear resistance at 23°C	good	• Temperature resistance short term	150 °C

Adhesion to Values

• ABS (initial)	14 N/cm	• PP (initial)	8.8 N/cm
• ABS (after 3 days)	14.8 N/cm	• PP (after 3 days)	10.5 N/cm
• PE (initial)	9 N/cm	• Steel (initial)	12.5 N/cm
• PE (after 3 days)	9.2 N/cm	• Steel (after 3 days)	14.6 N/cm

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=88676>