productinformation

tesa® 4952

Double-sided PE-foam mounting tape

tesa® 4952 is a double-sided PE-foam tape for constructive mounting applications. It consists of a highly conformable PE-foam backing and a tackified acrylic adhesive. tesa® 4952 has been externally certified for furniture mirror mounting.

Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

Main Application

- Furniture mirror mounting
- Mounting of car mirrors
- Mounting functional trims & profiles
- Mounting of decorative panels

Technical Data

•	Backing material	PE foam	•	Tensile strength	10 N/cm
•	Color	white	•	Type of liner	glassine
•	Total thickness	1150 μm	•	Colour of liner	brown
•	Type of adhesive	tackified acrylic	•	Thickness of liner	70 μm
	Elongation at break	200 %		Weight of liner	$80 g/m^2$

Adhesion to

 Aluminium (initial) PC (initial) PE (initial) PE (initial) PE (initial) PET (initial) PET (initial) PET (after 14 days) PET (after 14 days) PET (after 14 days) PPF (initial) PPF (after 14 days) 	•	Steel (initial)	6.5 N/cm	•	Steel (after 14 days)	8.0 N/cm
 PC (initial) PE (initial) PE (initial) PET (initial) PET (initial) PET (initial) PET (after 14 days) PET (after 14 days) PP (after 14 days) PS (after 14 days) PS (after 14 days) PS (after 14 days) 		ABS (initial)	5.0 N/cm	•	ABS (after 14 days)	8.0 N/cm
 PE (initial) PET (initial) PET (initial) PPT (after 14 days) PPT (a		Aluminium (initial)	5.0 N/cm	•	Aluminium (after 14 days)	8.0 N/cm
PET (initial) 5.0 N/cm PET (after 14 days) 7.0 N/c PP (initial) 2.8 N/cm PP (after 14 days) 5.5 N/c PS (initial) 5.0 N/cm PS (after 14 days) 7.5 N/c		PC (initial)	5.0 N/cm	•	PC (after 14 days)	8.0 N/cm
 PP (initial) PS (initial) 2.8 N/cm PP (after 14 days) PS (after 14 days) PS (after 14 days) 	•	PE (initial)	2.7 N/cm	•	PE (after 14 days)	2.8 N/cm
■ PS (initial) 5.0 N/cm ■ PS (after 14 days) 7.5 N/c		PET (initial)	5.0 N/cm	•	PET (after 14 days)	7.0 N/cm
		PP (initial)	2.8 N/cm	•	PP (after 14 days)	5.5 N/cm
 PVC (initial) 5.0 N/cm PVC (after 14 days) 8.0 N/c 	•	PS (initial)	5.0 N/cm	•	PS (after 14 days)	7.5 N/cm
		PVC (initial)	5.0 N/cm	•	PVC (after 14 days)	8.0 N/cm

For latest information on this product please visit http://l.tesa.com/?ip=04952

tesa® 4952

Double-sided PE-foam mounting tape

Properties

- Temperature resistance short term Temperature resistance long term
- Tack
- Humidity resistance
- Ageing resistance (UV)
- 80°C
- 80°C
- Resistance to chemicals
- Softener resistance
- Static shear resistance at 23°C
- Static shear resistance at 40°C



Evaluation across relevant tesa® assortment: • • • • very good good medium low

Additional Information

tesa® 4952 has been tested and approved by LGA institute for mirror mounting. Report number IWQ FSG 329 1189.

Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC