productinformation

tesa® 4982

100µm double sided transparent filmic tape

tesa® 4982 is a transparent double-sided self-adhesive tape consisting of a PET backing and a tackified acrylic adhesive.

tesa® 4982 features especially:

- Excellent bonding strength/thickness ratio
- Good bonding strength to most common, smooth, even substrates
- Reliable adhesion in high temperature applications

Main Application

- Mounting of backlight to LCD panel
- Mounting of LCD panel to metal frame
- Battery pack mounting

Technical Data

Backing material	PET film	Type of adhesive	tackified acrylic
Color	transparent	Elongation at break	50 %
Total thickness	100 μm	Tensile strength	20 N/cm

Adhesion to

•	Steel (initial)	8.2 N/cm	•	Steel (after 14 days)	11.7 N/cm
٠	ABS (initial)	7.6 N/cm		ABS (after 14 days)	9.6 N/cm
	Aluminium (initial)	7.9 N/cm		Aluminium (after 14 days)	10.6 N/cm
	PC (initial)	9.2 N/cm		PC (after 14 days)	11.0 N/cm
•	PE (initial)	4.6 N/cm		PE (after 14 days)	5.1 N/cm
	PET (initial)	7.0 N/cm		PET (after 14 days)	8.4 N/cm
	PP (initial)	4.4 N/cm		PP (after 14 days)	6.2 N/cm
٠	PS (initial)	8.3 N/cm		PS (after 14 days)	9.2 N/cm
	PVC (initial)	7.0 N/cm		PVC (after 14 days)	10.0 N/cm

Properties

	Temperature resistance short term	200 °C		Resistance to chemicals	• • •
	Temperature resistance long term	100 °C		Softener resistance	•••
	Tack	• •		Static shear resistance at 23°C	•••
	Ageing resistance (UV)	•••		Static shear resistance at 40°C	• • •
٠	Humidity resistance	•••			
Ev	aluation across relevant tesa® assortmen	t: ••• very good	•	● good ● ● medium ● low	

For latest information on this product please visit http://l.tesa.com/?ip=04982



tesa® 4982

100µm double sided transparent filmic tape

Additional Information

Liner variants: PV0 brown glassine paper (71 μ m; 82g/m²) PV6 red MOPP-film (80 μ m; 72g/m²)

Page 2 of 2 - as of 04/09/2019 -