



tesa® 4934

Product Information



Double-sided fabric tape

Product Description

tesa® 4934 is a double-sided tape. It consists of a fabric backing with a thick, tacky adhesive coating. The synthetic rubber adhesive is solvent free.

tesa® 4934 is a general purpose mounting tape.

tesa® 4934 is easily hand tearable.

Product Features

- The synthetic rubber adhesive is solvent free.
- tesa® 4934 is a general purpose mounting tape.
- tesa® 4934 is easily hand tearable.

Application Fields

Due to the flexible fabric backing and the high coating weight it is particularly suited for mounting on rough, fibrous surfaces, for example carpet laying.

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|------------------|-------------------|--------|
| • Backing | cloth | • Total thickness | 200 µm |
| • Type of adhesive | synthetic rubber | • Color | white |
| • Type of liner | glassine | | |

Properties/Performance Values

- | | | | |
|-----------------------------------|-----------|-------------------------------------|-----------|
| • Elongation at break | 20 % | • Static shear resistance at 40°C | very good |
| • Tensile strength | 35 N/cm | • Static shear resistance at 70°C | low |
| • Ageing resistance (UV) | medium | • Tack | very good |
| • Fogging | very good | • Temperature resistance long term | 40 °C |
| • Humidity resistance | good | • Temperature resistance short term | 60 °C |
| • Static shear resistance at 23°C | medium | | |



tesa[®] 4934

Product Information

Adhesion to Values

• PE (initial)	8 N/cm	• PVC (initial)	14 N/cm
• PE (after 14 days)	8.5 N/cm	• PVC (after 14 days)	22.5 N/cm
• PP (initial)	16 N/cm	• Steel (initial)	14.5 N/cm
• PP (after 14 days)	24.5 N/cm	• Steel (after 14 days)	24 N/cm

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=04934>