

tesafilm®

Product Information



59036, 59035, 59032, 59043, 59034, 59044, 59047, 59048, 59049

Sustainable Aspects

tesafilm® eco & crystal:

90% post consumer recycled PET (PCR PET) in film backing

core: 100% recycled plastic (PIR)

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|---------------------|-------------------|-------|
| • Backing | PET film | • Total thickness | 44 µm |
| • Type of adhesive | water-based acrylic | | |

Properties/Performance Values

- | | | | |
|--------------------------|---------|---------------------|------------------|
| • Elongation at break | 100 % | • Solvent free | yes |
| • Tensile strength | 43 N/cm | • Suitable surfaces | Paper, Cardboard |
| • Ageing resistance (UV) | yes | • Tear resistance | yes |
| • Hand tearability | no | • Transparency | good |
| • Low noise unwinding | yes | • Unwind force | 3 N/cm |
| • Photocopy neutral | yes | | |

Certificates

Certified according to

- INGEDI2
- UL ECVP 2809-2 (validity: 2023-08-25 to 2026-08-25, region(s): Offenburg, Germany)

tesafilm®

Product Information

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?cp=59032>