



**Product Information** 



# 90 $\mu$ m single-sided transparent PET filmic tape

### **Product Description**

The tackified acrylic adhesive gives this product outstanding removability without residue while using for temporary protection on surface. The 75  $\mu$ m transparent PET filmic backing offers excellent electrical insulation property. The PET liner ensures it can be easily released without adhesive residue.

# **Product Features**

- Easy removal without adhesive residue.
- Excellent electrical insulation property when it applies on surface with dielectric strength 132.1kV/mm.
- Easy for converting and die-cutting.

### **Application Fields**

• Electrical insulation with removability for temporary protection.

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

<ul><li>Backing</li><li>Type of adhesive</li><li>Type of liner</li></ul>	PET film tackified acrylic PET film	<ul><li>Total thickness</li><li>Color</li><li>Thickness of liner</li></ul>	90 μm transparent 36 μm
Properties/Performance Values			
<ul> <li>Elongation at break</li> <li>Chemical Resistance</li> <li>Dielectric breakdown voltage</li> <li>Easy to remove</li> </ul>	140 % medium 12000 V yes	<ul><li>Humidity resistance</li><li>Suitable for die cutting</li><li>Temperature resistance long term</li></ul>	very good yes 125 °C
Adhesion to Values			
Aluminium (initial)	0.16 N/cm	• Steel (initial)	0.22 N/cm





**Product Information** 

# Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit http://l.tesa.com/?ip=58346