



**Product Information** 



## Finely crêped paper masking tape for paint spraying

## **Product Description**

The product is thin and flexible and, therefore, suitable for all general masking applications, as well as oven drying applications up to a temperature of 80 °C.

## **Sustainable Aspects**



For more information: https://www.tesa.com/product-sustainability

## **Application Fields**

The product is resistant to wet sanding. Paints and fillers adhere well to the backing.

The material can be used on painted metal, rubber, glass and chrome parts.

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## **Product Construction**

<ul><li>Backing</li><li>Type of adhesive</li></ul>	slightly-creped paper natural rubber	<ul> <li>Bio-based content of liner by weight (acc. EN 16785)</li> <li>Total thickness</li> </ul>	55 % 140 μm
Properties/Performance Values			
<ul><li>Elongation at break</li><li>Tensile strength</li><li>Easy to remove</li></ul>	10 % 38 N/cm yes	<ul> <li>Hand tearability</li> <li>Temperature resistance (30 min)</li> <li>Temperature resistance (60 min)</li> </ul>	very good 100 °C 80 °C
Adhesion to Values			
• Steel	3.3 N/cm		





**Product Information** 

# Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 18/06/25 – en-SG