



# **Product Information**

## 100µm double sided black high performance filmic tape

#### **Product Description**

tesa® 61365 is a black, double sided self-adhesive tape consisting of a black PET backing and a tackified acrylic adhesive.

Special features:

- Thickness: 100µm
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- Excellent resistance to demanding environmental conditions
- Black color for easy detection or design purposes

## **Product Features**

- Thickness: 100µm
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- Excellent resistance to demanding environmental conditions
- Black color for easy detection or design purposes

# **Application Fields**

- Lens mounting in mobile phones
- Touch panel mounting

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

# **Product Construction**

- Backing
- Type of adhesive
- Type of liner
- Total thickness
- PET film tackified acrylic glassine 100 μm
  - Color of liner
    - Thickness of liner

Color

Weight of liner

black white with tesa logo 71  $\mu m$  80 g/m²





# **Product Information**

### **Properties/Performance Values**

<ul> <li>Elongation at break</li> <li>Tensile strength</li> <li>Ageing resistance (UV)</li> <li>Humidity resistance</li> </ul>	50 % 20 N/cm very good very good	<ul> <li>Static shear resistance at 40°C</li> <li>Tack</li> <li>Temperature resistance long term</li> <li>Temperature resistance short term</li> </ul>	good medium 100 °C 200 °C
Adhesion to Values			
<ul> <li>ABS (initial)</li> <li>ABS (after 14 days)</li> <li>Glass (initial)</li> <li>Glass (after 14 days)</li> <li>PC (initial)</li> </ul>	7.8 N/cm 11.2 N/cm 10.6 N/cm 13.1 N/cm 9 N/cm	<ul> <li>PC (after 14 days)</li> <li>PMMA (initial)</li> <li>PMMA (after 14 days)</li> <li>Steel (initial)</li> <li>Steel (after 14 days)</li> </ul>	17.7 N/cm 12.2 N/cm 16.7 N/cm 13.7 N/cm 16.5 N/cm

#### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

