



# tesa® 68552

## Product Information

50µm double sided transparent conformable filmic tape

### Product Description

tesa® 68552 is a transparent, doublesided self-adhesive tape consisting of a thin, conformable PET film backing and a tackified acrylic adhesive.

tesa® 68552 features esp.

- Thickness: 50 µm
- High adhesion level
- Excellent conformability and adjustment to curved surfaces
- Excellent resistance to demanding environmental conditions

### Application Fields

- Mounting of metal or plastic badges and signs
- Fixing of reflection foil to LCD frame
- Splicing of thin plastic films

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

- |                    |                   |                   |             |
|--------------------|-------------------|-------------------|-------------|
| • Backing          | PET film          | • Total thickness | 50 µm       |
| • Type of adhesive | tackified acrylic | • Color           | transparent |

### Properties/Performance Values

- |                          |           |                                     |        |
|--------------------------|-----------|-------------------------------------|--------|
| • Elongation at break    | 50 %      | • Static shear resistance at 23°C   | good   |
| • Tensile strength       | 7 N/cm    | • Static shear resistance at 40°C   | medium |
| • Ageing resistance (UV) | very good | • Tack                              | medium |
| • Chemical Resistance    | very good | • Temperature resistance long term  | 100 °C |
| • Humidity resistance    | very good | • Temperature resistance short term | 200 °C |



# tesa® 68552

## Product Information

### Adhesion to Values

• ABS (initial)	6.1 N/cm	• PET (after 14 days)	6.5 N/cm
• ABS (after 14 days)	7.3 N/cm	• PP (initial)	3 N/cm
• Aluminium (initial)	5.7 N/cm	• PP (after 14 days)	4.5 N/cm
• Aluminium (after 14 days)	7.4 N/cm	• PS (initial)	6 N/cm
• PC (initial)	7.4 N/cm	• PS (after 14 days)	7.7 N/cm
• PC (after 14 days)	8.9 N/cm	• PVC (initial)	6.3 N/cm
• PE (initial)	3.2 N/cm	• PVC (after 14 days)	10 N/cm
• PE (after 14 days)	4.2 N/cm	• Steel (initial)	7 N/cm
• PET (initial)	6.1 N/cm	• Steel (after 14 days)	8.6 N/cm

### Additional Information

Liner variants:

PV40 white/red logo glassine paper (71µm; 82g/m<sup>2</sup>)

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=68552>