



# tesa® 63610

## Product Information

1000µm double sided PE foam tape

### Product Description

tesa® 63610 is a double sided PE foam tape for mounting applications. It consists of a highly conformable PE foam backing and a tackified acrylic adhesive.

Product benefits:

- High ultimate adhesion level for a reliable bonding performance
- Fully outdoor suitable, UV, water and aging resistance
- Conformable PE foam core with high inner strength
- Suitable for automatic and manual module assembly
- Easy solar module assembly due to a high foam compression rate

### Application Fields

- Mounting of solar module frames
- Mounting of trims and profiles
- General mounting applications

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

### Product Construction

- |                    |                   |                   |             |
|--------------------|-------------------|-------------------|-------------|
| • Backing          | PE foam           | • Total thickness | 1000 µm     |
| • Type of adhesive | tackified acrylic | • Color           | black/white |



# tesa® 63610

## Product Information

### Properties/Performance Values

• Elongation at break	180 %	• Static shear resistance at 70°C	medium
• Tensile strength	8 N/cm	• Tack	medium
• Ageing resistance (UV)	very good	• Temperature resistance long term	80 °C
• Static shear resistance at 23°C	medium	• Temperature resistance short term	80 °C
• Static shear resistance at 40°C	medium		

### Adhesion to Values

• ABS (initial)	8 N/cm	• PET (after 14 days)	11 N/cm
• ABS (after 14 days)	11 N/cm	• PP (initial)	0.9 N/cm
• Aluminium (initial)	8 N/cm	• PP (after 14 days)	1.5 N/cm
• Aluminium (after 14 days)	11 N/cm	• PS (initial)	8 N/cm
• PC (initial)	8 N/cm	• PS (after 14 days)	11 N/cm
• PC (after 14 days)	11 N/cm	• PVC (initial)	6 N/cm
• PE (initial)	0.9 N/cm	• PVC (after 14 days)	11 N/cm
• PE (after 14 days)	1.5 N/cm	• Steel (initial)	11 N/cm
• PET (initial)	8 N/cm	• Steel (after 14 days)	11 N/cm

### Additional Information

Liner variants:

- PV50 transparent PET film (50 µm)
- PV15 blue PE film (100 µm)
- PV20 yellow glassine paper (70 µm)

Peel Adhesion:

- immediately: foam splitting on steel
- after 14 days: foam splitting on steel, ABS, Aluminum, PC, PET, PS, PVC

tesa® 63610 is recognized by UL as photovoltaic polymeric material (QIHE2).

tesa® 63610 has been tested by TÜV Rheinland. The test confirms the longterm adhesion performance after IEC 61215 climate tests and a 85°C temperature resistance.

The temperature resistance (short/long) of tesa® 63610 has been approved according to tesa test method under static load.



# tesa® 63610

## Product Information

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=63610>