



Product Information

1,000 μ m single sided grey electrically conductive foam tape

Product Description

tesa[®] 60216 is a grey single sided electrically conductive self adhesive foam tape. It consists of a highly compressible electrically conductive foam backing and an electrically conductive adhesive.

tesa® 60216 features especially:

- Thickness: 1,000 μm
- · Highly compressible foam backing with low closure force and reliable recovery properties
- Excellent conformability to surface variations and tolerances
- Excellent electrical conductivity over a wide working range in XYZ-direction even at high temperatures and humidity
- · High adhesion level even at harsh environmental conditions
- Excellent shock absorbing and cushioning properties
- High stability of the foam to avoid flaking of particles

Product Features

- Thickness: 1,000 μm
- · Highly compressible foam backing with low closure force and reliable recovery properties
- Excellent conformability to surface variations and tolerances
- Excellent electrical conductivity over a wide working range in XYZ-direction even at high temperatures and humidity
- · High adhesion level even at harsh environmental conditions
- Excellent shock absorbing and cushioning properties
- · High stability of the foam to avoid flaking of particles

Application Fields

- EMI shielding and grounding applications
- Electrostatic discharge applications

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- Backing
- Type of adhesive
- Type of liner
- Total thickness
- conductive foam conductive acrylic PE-coated paper 1000 µm
- ColorColor of liner
- Thickness of liner

grey white/blue logo 120 μm

For latest information on this product please visit http://l.tesa.com/?ip=60216





Product Information

Properties/Performance Values

•	Contact resistance z-direction	0.03 Ohm / square
	(initial)	inch
•	Release of liner	easy

- Adhesion to Values
- Steel (after 14 days)
 8.5 N/cm

- Surface resistance x-y-direction 0.2 m
- Temperature resistance short 20
 term
- 0.2 mOhm

200 °C

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

