

# tesa<sup>®</sup> 75410

## Product Information



100µm double sided black flexible acrylic foam tape

## Product Description

tesa<sup>®</sup> 75410 is a double-sided black tape consisting of a high shock absorbing black acrylic foam.

tesa<sup>®</sup> 75410 features:

- \* Thickness: 100µm
- \* Very high shock performance
- \* Very high thermal shock resistance
- \* Very high bonding strength
- \* Anti-repulsion properties to prevent lifting
- \* Waterproofing
- \* Light blocking in x/y direction

## Application Fields

- Demanding mounting applications with high requirements for impact resistance
- \* Mounting of components
- \* Mounting with ultra slim die-cut designs
- \* Mounting of waterproof designs

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

## Product Construction

- |                    |                  |                      |             |
|--------------------|------------------|----------------------|-------------|
| • Type of adhesive | modified acrylic | • Color              | black       |
| • Type of liner    | PET              | • Color of liner     | transparent |
| • Total thickness  | 100 µm           | • Thickness of liner | 50 µm       |

# tesa<sup>®</sup> 75410

## Product Information

### Properties/Performance Values

- Static shear resistance at 23°C    good
- Static shear resistance at 40°C    good

### Adhesion to Values

- |                            |           |                        |           |
|----------------------------|-----------|------------------------|-----------|
| • Aluminium (initial)      | 7.2 N/cm  | • PC (initial)         | 9.8 N/cm  |
| • Aluminium (after 3 days) | 9.4 N/cm  | • PC (after 3 days)    | 12.3 N/cm |
| • Glass (initial)          | 11.4 N/cm | • Steel (initial)      | 11.6 N/cm |
| • Glass (after 3 days)     | 11.9 N/cm | • Steel (after 3 days) | 13.1 N/cm |

## Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=75410>