

# tesa® 4309 Roll Masker Light

## **Product Information**



Economic overmasking solution for 2-tone paintings with medium oven temperatures

## **Product Description**

tesa RollMasker 4903 LT is a combination of 4309-tape and HDPE-film for large area maskings during mulitcolor car paintings in the paint shop at automotive OEMs.

The combination of tape and film reduces process times and material waste at the OEM compared to a stand-alone filmic hood. It ensures an efficient and reliable masking process with a temperature resistance of up to 120°C/1h. Thus, it can be used at paintings with wet-demasking processes or medium temperature oven temperatures.

Besides, it offers the following features:

- \* Tear resistant paper masking tape enable quick de-masking drying
- \* Statical loading of film eliminates risk of overspray as well as paint deformations on the car body
- \* tesa dispenser available for roll masker

#### **Product Features**

- Tear resistant paper masking tape enable quick de-masking drying
- · Statical loading of film eliminates risk of overspray as well as paint deformations on the car body
- · tesa dispenser available for roll masker
- It ensures an efficient and reliable masking process with a temperature resistance of up to 120°C/1h
- The combination of tape and film reduces process times and material waste at the OEM compared to a stand-alone filmic hood.

### **Application Fields**

- · Car body masking
- \* Efficient overmasking
- \* Bumper masking without flaming or powerwash requirements
- \* Large area masking at low to medium temperatures
- \* Masking with wet de-masking processes



## tesa® 4309 Roll Masker Light

## **Product Information**

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

<ul> <li>Bac</li> </ul>	king	Paper •	Total thickness	170 μm
-------------------------	------	---------	-----------------	--------

Type of adhesive natural rubber

## **Properties/Performance Values**

•	Elongation at break	12 %	•	Material of masking coverage	HDPE
•	Tensile strength	47 N/cm	•	Thickness of masking coverage	20 μm

## Adhesion to Values

• Steel 3.5 N/cm

### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

