



Product Information



8.7 N/cm

13 N/cm

10.2 N/cm

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

Product Construction			
BackingType of adhesiveType of liner	non-woven tackified acrylic PE-coated paper	Total thicknessColorColor of liner	160 μm translucent white/blue logo
Properties/Performance Values			
 Elongation at break Tensile strength Removability after 14 days (23°C) Residue-free removability 	25 % 20 N/cm good yes	 Static shear resistance at 23°C Tack Temperature resistance long term Temperature resistance short term 	very good medium 80 °C 160 °C
Adhesion to Values			
 ABS (initial) ABS (after 3 days) Aluminium (initial) Aluminium (after 3 days) Glass (initial) Glass (after 3 days) 	8.6 N/cm 11 N/cm 9.2 N/cm 11.3 N/cm 9.2 N/cm 9.8 N/cm	 PMMA (initial) PMMA (after 3 days) PP (initial) PP (after 3 days) PS (initial) PVC (initial) 	9.9 N/cm 11.3 N/cm 5 N/cm 6.7 N/cm 10 N/cm 7.8 N/cm

• Steel (initial)

Steel (after 14 days)

• Steel (after 3 days)

- Glass (after 3 days) • • PC (initial) 8.5 N/cm • PC (after 3 days) 9.2 N/cm 8.4 N/cm
- PET (initial)





Product Information

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



Page 2 of 2 – as of 24/07/25 – en-SG