

tesa® 88648

Product Information

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

• Backing	non-woven	• Total thickness	160 µm
• Type of adhesive	tackified acrylic	• Color	translucent
• Type of liner	PE-coated paper	• Color of liner	white/blue logo

Properties/Performance Values

• Elongation at break	25 %	• Static shear resistance at 23°C	very good
• Tensile strength	15 N/cm	• Tack	good
• Removability after 14 days (23°C)	good	• Temperature resistance long term	80 °C
• Residue-free removability	yes	• Temperature resistance short term	130 °C

Adhesion to Values

• ABS (initial)	9 N/cm	• Steel (initial)	9 N/cm
• ABS (after 3 days)	10 N/cm	• Steel (after 14 days)	11 N/cm
• PP (initial)	6 N/cm	• Steel (after 3 days)	10 N/cm
• PP (after 3 days)	7 N/cm		

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit <http://l.tesa.com/?ip=88648>