# tesa® 60260



# **Product Information**

## 35µm double sided grey electrically conductive non-woven tape

tesa® 60260 is an ultra-thin grey double sided electrically conductive self adhesive tape. It consists of an electrically conductive non-woven backing and an electrically conductive acrylic adhesive.

tesa® 60260 features especially:

- Thickness: 35μm
- · Excellent electrical conductivity in XYZ-direction even at high temperatures and humidity
- · High adhesion level even at harsh environmental conditions
- · Excellent conformability and adjustment to uneven surfaces
- Very good die-cuttability

### Main Application

- · EMC applications, such as grounding
- Electrostatic discharge applications

## Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Technical Data**

<ul> <li>Backing material</li> </ul>	conductive non-	<ul> <li>Thickness of liner</li> </ul>	50 μm
	woven	<ul> <li>Release of liner</li> </ul>	easy
<ul> <li>Color</li> </ul>	grey	<ul> <li>Temperature resistance short</li> </ul>	200 °C
<ul> <li>Total thickness</li> </ul>	35 μm	term	
<ul> <li>Type of adhesive</li> </ul>	conductive acrylic	<ul> <li>Contact resistance z-direction</li> </ul>	0.02 Ohm / square
<ul> <li>Type of liner</li> </ul>	PET film	(initial)	inch
<ul> <li>Colour of liner</li> </ul>	transparent	Surface resistance x-y-direction	0.2 Ohm / square
Adhesion to			
<ul> <li>Steel (initial)</li> </ul>	4 0 N/cm	<ul> <li>Steel (after 14 days)</li> </ul>	4.2 N/cm

• Steel (Illitial)	4.0 N/CIII	• Steer (after 14 days)	4.2 N/CIII

#### **Properties**

Static shear resistance at 23°C
 Static shear resistance at 40°C

Evaluation across relevant tesa® assortment: •••• very good ••• good •• medium • low

# tesa® 60260



# **Product Information**

#### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

