

# tesa® 66022 low VOC



**Product Information** 

 $220 \mu m$  reinforced water based acrylic adhesive layer with PET scrim for mounting in automotive interiors

### **Product Description**

tesa® 66022 is a conformable transparent adhesive layer of water based acrylic reinforced with a PET scrim mesh.

Features:

\*very low total VOC values and no critical substances detectable
\*high initial tack and peel adhesion
\*high conformable design following 3D shapes
\*provides excellent conformability and stability
\*provides excellent initial adhesion to a wide variety of interior substrates
\*suitable for the bonding to nonpolar plastics, foams, felts and fabrics
\*suitable for a certain gap filling due to thick adhesive layer
\*reliable adhesion performance for the whole vehicle life time
\*the scrim provides a reinforcement of flexible substrates for improving converting efficiency and handling

## **Application Fields**

immediate secure fixation of light, stiff, rigid, rough parts in vertical and horizontal position e.g. energy absorber mounting (HIC, crash pad ...) mounting of plastics as well LSE plastics \*with difficult wet-out \*permanent low load Lamination or mounting of critical, soft, light and smooth surfaces / sheets \*immediate and secure bending around the edge

### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

Type of liner	glassine	Color	transparent					
<ul> <li>Backing material</li> </ul>	none	Colour of liner	brown/blue logo					
Type of adhesive	water-based acrylic	Thickness of liner	71 µm					
Dreparties/Deutermannes Malues								

### Properties/Performance Values

٠	Low VOC	very good	•	Temperature resistance max.	200 °C
٠	Suitable for rough surfaces	very good	٠	Temperature resistance min.	-40 °C
•	Tack	very good			



# tesa® 66022 Iow VOC

# **Product Information**

### Adhesion to Values

	ABS (initial) ABS (after 3 days)			PP (initial) PP (after 3 days)	14 N/cm 16 N/cm
	PC (initial)			PS (initial)	17.7 N/cm
	PC (after 3 days)			PVC (initial)	12 N/cm
•	PE (initial)	9.2 N/cm	٠	Steel (initial)	12.3 N/cm
•	PET (initial)	16.2 N/cm	•	Steel (after 3 days)	17.3 N/cm
•	PET (after 3 days)	18.1 N/cm			

#### **Additional Information**

Is designed to fulfill the low VOC (Volatile Organic Compounds) automotive requirements set forth by the Japanese Ministry of Health, Labor and Welfare (MHLW) and the Japanese Automobile Manufacturers Association (JAMA) limit of concentrations of 13 toxic chemistries. Acc. Toyota TSK0508G our assortment is conform Japanese automotive requirements

Adhesion vaules to:

PVC PP ABS PC PET PS PE Are not part of the product specification

PV20 brown glassine liner / blue tesa logo other liner version possible - on request

### Disclaimer

tesa<sup>®</sup> products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa<sup>®</sup> product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.