



tesa® 61335

Product Information

200µm double sided black high performance filmic tape

Product Features

- Thickness: 200µm
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- Easy handling and processing performance due to very strong PET backing
- Excellent resistance to demanding environmental conditions
- Black colour for easy detection or design purposes

tesa® 61335 is a black, double sided self-adhesive tape consisting of a thick black PET backing and a tackified acrylic adhesive.

Special features:

- Thickness: 200µm
- Very high bonding strength
- Superior push out resistance
- High shock resistance
- Easy handling and processing performance due to very strong PET backing
- Excellent resistance to demanding environmental conditions
- Black colour for easy detection or design purposes

Product Construction

• Type of adhesive	tackified acrylic	• Total thickness	200 µm
• Type of liner	glassine	• Thickness of liner	71 µm
• Colour of liner	white with tesa logo	• Backing material	PET film
• Weight of liner	80 g/m ²	• Color	black

Product Properties/Performance Values

• Elongation at break	60 %	• Ageing resistance (UV)	very good
• Static shear resistance at 23°C	good	• Static shear resistance at 40°C	good
• Humidity resistance	++	• Temperature resistance long term	100 °C
• Tack	medium	• Temperature resistance short term	200 °C
• Tensile strength	110 N/cm		



tesa® 61335

Product Information

Adhesion to Values

• Steel (initial)	15.5 N/cm	• PC (initial)	12.7 N/cm
• PC (after 14 days)	20.9 N/cm	• Glass (after 14 days)	20.5 N/cm
• Steel (initial)	15.5 N/cm	• Glass (initial)	15.8 N/cm
• PMMA (after 14 days)	18.5 N/cm	• PMMA (initial)	16.8 N/cm
• ABS (initial)	11.9 N/cm	• Steel (after 14 days)	18.6 N/cm
• ABS (after 14 days)	18.9 N/cm		

Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.



For latest information on this product please visit
<http://l.tesa.com/?ip=61335>