

# tesa® ACXplus 77115

### **Product Information**



Double-sided high performance acrylic foam tape

# **Product Description**

tesa® ACX<sup>plus</sup> 77115 is a high performance double-sided acrylic foam tape for exterior attachment part mounting. Its outstanding wide temperature range resistance is based on its well-balanced pure acrylic core and tackified adhesive, which assure reliable bonding of the part for the entire life of the vehicle.

Due to the product's unique formulation, it has the ability to absorb and dissipate the stress on the bonding line and builds up its wetting on the substrate.

Also available in 0.8 mm and 1.2 mm formats.

#### Main features

- Excellent shear resistance at elevated temperatures
- Superior wet-out performance for high initial bonding on MSE substrates
- · High humidity, gasoline, and UV resistance
- · Viscoelastic acrylic foam core to compensate for different thermal elongation of bonded parts
- · Closed cell acrylic foam core for reliable sealing to prevent water penetration

# **Application Fields**

tesa® ACX<sup>plus</sup> 77115 is suitable for a wide range of exterior mounting applications.

Example applications are the permanent exterior mounting of:

- \* Body side moldings and decorative trims
- \* Emblems
- \* Spoilers
- \* Antennas
- \* Pillar appliques

To ensure the highest performance possible, our aim is to fully understand your application (including the substrates involved) in order to provide the right product recommendation.



# tesa® ACXplus 77115

### **Product Information**

#### Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

#### **Product Construction**

•	Backing material	foamed acrylic	•	Total thickness	1500 μm
•	Type of adhesive	tackified acrylic	•	Color	black

#### **Properties/Performance Values**

<ul> <li>Ageing resistance (UV)</li> <li>very good</li> </ul>	lemperature range	-40 to +80 °C
---	-------------------	---------------

#### Adhesion to Values

ABS (after 3 days)	29 N/cm	<ul> <li>Steel (after 3 days)</li> </ul>	34 N/cm

#### **Additional Information**

PV 26 = White siliconized PE-coated paper liner

PV 28 = Blue silicone free filmic HDPE liner

#### Disclaimer

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.